10

15

## Patent Claims

- 1. A method of making porous near-net-shape metallic and/or ceramic parts with an open porosity of at least 10% by volume according to the steps of:
- a) forming an injectable mass of metallic and/or ceramic powder, at least one thermoplastic binder, and at least one place holder:
- b) injection molding the mass into the shape of the part to be produced;
- c) cooling the injection-molded mass and setting it in a capillary-active material and subjecting it to a first-stage binder removal to produce an open porosity;
- d) removing the place holder at least partially from the part with a fluid;
- e) subjecting the part to a thermal binder-removing process;
  - f) subsequently sintering the part.
- 2. The method according to claim 1 wherein the place holder is NaCl, KCl, K<sub>2</sub>CO<sub>3</sub>, or Na<sub>2</sub>CO<sub>3</sub>.
- 20 3. The method according to claim 1 or 2 wherein the metal powder is stainless steel, Ti, NiTi, or a titanium alloy.

10

15

- 4. The method according to claims 1 to 3 wherein between steps c) and d) there is a thermal binder-removing step.
- 5. The method according to claim 4 wherein the thermal binder-removing step is conducted at a temperature up to 270°C under a protective-gas atmosphere.
- 6. The method according to claims 1 to 5 wherein the starting powder has a particle size of less than 20  $\mu m$ .
- 7. The method according to claims 1 to 6 wherein the thermal binder-removing step is conducted at a temperature up to 500°C and under a protective-gas atmosphere.
- 8. The method according to claims 2 to 7 wherein a fluid heated up to 50°C is used.
- 9. The method according to claims 1 to 8 wherein the fluid for removing the place holder is water.
- 10. The method according to claim 1 wherein a stirred water bath is used in order to remove the place holder.
- 11. The method according to claims 1 to 10 wherein the thermal binder-removing step uses argon as a protective gas.

12. The method according to claims 1 to 11 wherein an open porosity in the part is produced of at least 30% by volume, in particular 50% by volume.